

University of Groningen

Superconductivity at 18 K in potassium-doped C60

Hebard, A.F.; Rosseinsky, M.J.; Haddon, R.C.; Murphy, D.W.; Glarum, S.H.; Palstra, T.T.M.; Ramirez, A.P.; Kortan, A.R.

Published in:
Nature

DOI:
[10.1038/350600a0](https://doi.org/10.1038/350600a0)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1991

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Hebard, A. F., Rosseinsky, M. J., Haddon, R. C., Murphy, D. W., Glarum, S. H., Palstra, T. T. M., Ramirez, A. P., & Kortan, A. R. (1991). Superconductivity at 18 K in potassium-doped C60. *Nature*, 350(6319).
<https://doi.org/10.1038/350600a0>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Superconductivity at 18 K in potassium-doped C_{60}

A. F. Hebard, M. J. Rosseinsky, R. C. Haddon,
D. W. Murphy, S. H. Glarum, T. T. M. Palstra,
A. P. Ramirez & A. R. Kortan

AT&T Bell Laboratories, Murray Hill, New Jersey 07974-2070, USA

THE synthesis of macroscopic amounts of C_{60} and C_{70} (fullerenes)¹ has stimulated a variety of studies on their chemical and physical properties^{2,3}. We recently demonstrated that C_{60} and C_{70} become conductive when doped with alkali metals⁴. Here we describe low-temperature studies of potassium-doped C_{60} both as films and bulk samples, and demonstrate that this material becomes superconducting. Superconductivity is demonstrated by microwave, resistivity and Meissner-effect measurements. Both polycrystalline powders and thin-film samples were studied. A thin film showed a resistance transition with an onset temperature of 16 K and essentially zero resistance near 5 K. Bulk samples showed a well-defined Meissner effect and magnetic-field-dependent microwave absorption beginning at 18 K. The onset of superconductivity at 18 K is the highest yet observed for a molecular superconductor.

The sensitivity to air of alkali-metal-doped fullerenes (A_xC_n) limits the choice of sample preparation and characterization techniques. To avoid sample degradation, we carried out reactions with the alkali metal vapour and C_{60} in sealed tubes either in high vacuum or under a partial pressure of helium. The C_{60} was purified by chromatography¹ of fullerite² and was heated at 160 °C under vacuum to remove solvents.

Small amounts of the individual fullerenes (~0.5 mg) were placed in quartz tubes with alkali metals and sealed under vacuum. These samples were subjected to a series of heat treatments and tests for superconductivity by 9-GHz microwave-loss experiments⁵. Preliminary tests indicated that only the K-doped C_{60} showed a response consistent with a superconducting transition (Fig. 1). For this reason, together with the fact that K_xC_{60} showed the highest film conductivity¹, we focused our studies on the K-doped compound.

The conductivity measurements were performed on potassium-doped films of C_{60} that were prepared in a one-piece all-glass version of the apparatus described previously⁴. This reaction vessel was sealed under a partial pressure of helium

before reaction. This configuration allowed both *in situ* doping and low-temperature studies of thin films. All measurements were made in a four-terminal Van der Pauw configuration using a 3- μ A a.c. current at 17 Hz. Figure 2 shows the temperature dependence of the resistivity of a 960-Å-thick K_xC_{60} film. The film was doped with potassium until the resistivity had fallen to $5 \times 10^{-3} \Omega \text{ cm}$. The resistivity increases by a factor of two on cooling the sample to near 20 K. Below 16 K, the resistivity starts to decrease; zero resistivity ($<10^{-4}$ of the normal state) is obtained below 5 K. The 10–90% width of the transition is 4.6 K. At 4 K we measured the lower bound to the critical current to be 40 A cm^{-2} .

A bulk polycrystalline sample of nominal composition K_3C_{60} was prepared by reaction of 29.5 mg of C_{60} with 4.8 mg potassium. The amount of potassium was controlled volumetrically by using potassium-filled pyrex capillary tubing cut to size in a dry box. The reaction was run with the C_{60} in a 5-mm fused silica tube joined to a larger tube in which the potassium-containing capillary was placed. The tube was sealed after being evacuated and refilled with 10^{-2} torr of helium to serve later as a thermal-exchange gas for low-temperature measurements. With the C_{60} -containing end of the tube at room temperature,




FIG. 1 Microwave loss as a function of temperature for K_xC_{60} in a static field of 20 Oe.




FIG. 2 Temperature dependence of the electrical resistivity of a 960-Å-thick film of K_xC_{60} .

the potassium was distilled from the capillary in a furnace at 200 °C. Some reaction of the potassium with the quartz tube, visible as a dark brown discoloration, was observed at this temperature. Unreacted potassium was observed after this period. Following distillation of the potassium to the C_{60} end, the tube was shortened by sealing to about 8 cm and heated to 200 °C for 36 h. Finally, the tube was resealed to a length of about 4 cm for magnetic measurements.

The temperature dependence of the d.c. magnetization of the sample with nominal composition K_3C_{60} was measured in a SQUID magnetometer (Fig. 3). On zero-field cooling the sample to 2 K, a magnetic field of 50 Oe was applied. On warming, this field is excluded by the sample to 18 K; this verifies the presence of a superconducting phase. The bulk nature of superconductivity in the sample is demonstrated unambiguously by cooling in a field of 50 Oe. A well defined Meissner effect (flux expulsion) develops below 18 K. The shape of the magnetization curve, in particular the temperature-independent signal at low temperature, indicates good superconducting properties for this sample. Also noteworthy is the relatively narrow transition width. The magnitude of the flux exclusion for the zero-field-cooled curve corresponds to 1% volume fraction. This small fraction is possibly due to non-optimal doping or the granular nature of the sample. The large value of the Meissner effect for the field-cooled curve relative to the total exclusion, however,




FIG. 3 Temperature dependence of the magnetization of a K_xC_{60} crystalline sample. The direction of temperature sweep in the field-cooled (FC) and the zero-field-cooled (ZFC) curves is indicated by the arrows.

indicates bulk superconductivity in the electrically connected regions.

The universally accepted tests for superconductivity, namely a transition to zero resistance and a Meissner effect showing the expulsion of magnetic field, demonstrate unequivocally the existence of superconductivity in K_xC_{60} . The 18-K transition temperature is the highest yet reported for a molecular superconductor. This may be compared with the previously reported occurrence of superconductivity at 0.55 K in potassium-intercalated graphite⁶. We expect that optimization of composition and crystallinity will lead to further improvement in the superconducting properties. □

Received 26 March; accepted 4 April 1991.

1. Kroto, H. W., Heath, J. R., O'Brien, S. C., Curl, R. F. & Smalley, R. E. *Nature* **318**, 162-164 (1985).
2. Kratschmer, W., Lamb, L. D., Fostiropoulos, K. & Huffman, D. R. *Nature* **347**, 354-358 (1990).
3. Meijer, G. & Bethune, D. S. *J. chem. Phys.* **93**, 7800-7802 (1990).
4. Haddon, R. C. *et al.* *Nature* **350**, 320-322 (1991).
5. Haddon, R. C., Glarum, S. H., Chichester, S. V., Ramirez, A. P. & Zimmerman, N. M. *Phys. Rev. B* **43**, 2642-2647 (1991).
6. Hannay, N. B. *et al.* *Phys. Rev. Lett.* **14**, 225-226 (1965).

ACKNOWLEDGEMENTS. We thank G. Dabbagh, S. J. Duclos, R. H. Eick, A. T. Flory, R. M. Fleming, M. L. Kaplan, K. B. Lyons, A. V. Makhija, B. Miller, A. J. Muller, K. Raghavachari, J. M. Rosamilia, L. F. Schneemeyer, F. A. Thiel, J. C. Tully, R. Tycko, R. B. Van Dover, J. V. Waszczak, W. L. Wilson and S. M. Zahurak for valuable contributions to this work.